



OPTICAL DEPOSITION LABORATORY

Specification for “MAGENTA”

Issued: 12/07/2004

Page 1 of 2

Confidential Clause:

This document is the property of O.D.L. S.p.A. Not to be handed over to, copied, or used by third party. Any reproduction of contents has to be authorized by O.D.L. S.p.A. in writing.



OPTICAL DEPOSITION LABORATORY

Technical Data:

$T_{avg.} \geq 87\%$ for $420nm < \lambda < 440nm$

$T = 50\%$ $475nm \pm 3\%$

$T_{avg.} \leq 10\%$ for $505nm < \lambda < 580nm$

$T = 50\%$ $620nm \pm 3\%$

$T_{avg.} \geq 85\%$ $640nm < \lambda < 700nm$

$i = 0^\circ$

TLM630

